

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
30 June 2005 (30.06.2005)


PCT

(10) International Publication Number
WO 2005/059645 A2

- (51) International Patent Classification⁷: **G03F**
- (21) International Application Number:
PCT/EP2004/014100
- (22) International Filing Date:
10 December 2004 (10.12.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/530,623 19 December 2003 (19.12.2003) US
60/568,006 4 May 2004 (04.05.2004) US
- (71) Applicant (for all designated States except US): **CARL ZEISS SMT AG** [DE/DE]; Carl Zeiss Str. 22, 73447 Oberkochen (DE).
- (72) Inventor; and
(75) Inventor/Applicant (for US only): **SCHUSTER, Karl-Heinz** [DE/DE]; Rechbergstrasse 24, 89551 Königsbronn (DE).
- (74) Agent: **MÜLLER-RISSMANN, Werner**; c/o Carl Zeiss AG, Patentabteilung, 73446 Oberkochen (DE).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH,

[Continued on next page]

(54) Title: MICROLITHOGRAPHY PROJECTION OBJECTIVE WITH CRYSTAL ELEMENTS



(57) Abstract: A microlithography projection objective is proposed with optical elements, i.e. lenses or planar-parallel plates (used as end-closure plates) of crystalline magnesium fluoride, quartz, lanthanum fluoride, sapphire and Alpha-aluminium oxide. Suitable crystallographic orientations, crystal 10 combinations, and polarizations of the light are described. Suitable applications are for immersion lithography or near-field lithography in the DUV and VLN range, using the highest numerical aperture values.



GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, NA,

SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations
- of inventorship (Rule 4.17(iv)) for US only

Published:

- without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Microlithography Projection Objective with Crystal Elements

5 The invention relates to a microlithography projection
objective with crystal elements, namely such made from
materials showing birefringence and other than cubic crystal
structure.

10 These are of relevance mainly as some of them show refractive
indices well above those of quartz glass or calcium fluoride,
what is a substantial need for immersion lithography with
image side numerical apertures beyond 1.0 up to about 2 or
more.

15 From publications such as

Bruce W. Smith et al. Optical Microlithography XVII
Proc. SPIE 5377 (2004), p 273 -284;

20 Bruce W. Smith et al. Optical Microlithography XVI,
Proc. SPIE 5040 (2003), p 679 -689;

John H. Burnett et al. "High Index Materials for 193 nm and
157 nm Immersion lithography"
25 Int'l Symp. on Immersion & 157 nm Lithography, Vancouver
8/2/04 (NIST/ Corning Tropel)

and patent applications such as
WO2004/019 128 A2,
30 or, commonly owned with this application:
US 6,717,722 B,
US Ser. No. 10/734,623 filed 15 Dec. 2003,
US Ser. No. 60/530,623 filed 19 Dec. 2003,
US Ser. No. 60/530,978 filed 22 Dec. 2003,
35 US Ser. No. 60/544,967 filed 13 Feb. 2004,
US Ser. No. 60/568,006 filed 04 May 2004,
US Ser. No. 60/592,208 filed 29 July 2004,
US Ser. No. 60/591,775 filed 27 July 2004,
US Ser. No. 60/612,823 filed 24 Sept 2004,
40 DE 10 2004 051 730.4 filed 22 Oct. 2004

some information about this art can be gathered.

45 Of these, e. g. WO 2004/019 128 A2, US 10/734,623,
US 60/592,208, US 60/591,775 and US 60/612,823 show objective
designs which can be optimized by and combined with the use
of materials and teachings according to this application.

Suitable immersion liquids are inter alia described in US
50 60/568,006 or DE 10 2004 051 730.4.

All cited documents are incorporated into this application by reference in their entirety.

- 5 Their citation in no way constitutes any declaration on their relevance for this application, and the list certainly is incomplete and many more publications relate to this art.

□

- For end-closure plates or for the last-positioned lens
10 element in immersion objectives or near-field objectives there is a need for optical materials of the highest possible index of refraction. At the same time, the materials need to be transparent, homogeneous, radiation-resistant, as well as mechanically and chemically robust. There is a material
15 which meets all of these conditions except for optical isotropy. The material is sapphire or, in chemical terms, Al_2O_3 . Others are MgF_2 or LaF_3 and other uniaxial crystals.

- In an absolutely telecentric light path and with completely
20 tangential polarization it is possible to achieve complete isotropy of the light-transmitting properties by using the measures proposed by the present invention.

- The claims together with this specification describe
25 solutions to these problems and advantageous varieties.

- Figures 1 to 8 and 10 to 13 are sketches that illustrate the principles of arrangements, or parts thereof, according to the invention.

- 30 Figure 9 shows wavelength-dependent variation of n_e and n_o for some materials from an article.

- In the illustrated arrangements, for example in Figure 2, the
35 sum $(n_o - n_e)\text{Al}_2\text{O}_3 + (n_o - n_e)\text{SiO}_2$ equals zero for a maximum-aperture

ray B_{\max} with an incident angle of 70° (n_o refractive index of ordinary ray, n_e refractive index of extraordinary ray).

The following symbols are used in the drawings:

5

AS = aperture stop / system aperture

P = protector plate / protective element

I = immersion fluid, immersion

W = wafer, or the object to be exposed in the image plane

10

OA = optical axis

L = lens

B_{\max} = ray of maximum aperture

With tangential polarization of the light rays there is only
15 one component, namely the p-component, and as a consequence,
there is no phase shift between p- and s-components as long
as the optical crystal axis of the crystal is oriented in
exact parallel alignment with the optical axis of the
objective. However, these conditions are met only
20 approximately in practical cases. As a means to achieve
perfect isotropy in the effect that a plate of this kind has
on light rays, it is proposed according to the present
invention that the plate be made of two parts. The proposed
combination consists of an Al_2O_3 sapphire plate P_1 of optically
25 negative character and an SiO_2 crystal plate P_2 of optically
positive character, as illustrated in Figures 1 to 3. The
magnitude of the birefringence changes individually with the
wavelength. The plate thicknesses are therefore selected
dependent on the wavelength, so that a birefringence of the
30 Al_2O_3 plate is compensated by the complementary birefringence
of the SiO_2 plate. This cannot be achieved completely,
because the indices of refraction are different for the two
materials, so that a compromise is necessary for different
incident light angles. However, an exact compensation can be

achieved in particular for the highest apertures which are relevant in immersion lithography applications, e.g., for dipole illumination.

5 In addition to a planar plate, the invention can also be used in a lens element. Since Al_2O_3 sapphire offers one of the highest known indices of refraction for the wavelengths of 157 nm and 193 nm, it is a preferred material to use for the element in the last position of the objective. Elements of
10 crystalline SiO_2 are placed (in direction of light propagation) before the Al_2O_3 element.

Figure 4 represents a sketch to illustrate the principle, wherein the symbol QG stands for quartz glass, QK for quartz
15 crystal, S for sapphire (which is at the same time a lens L in the sense of Figure 1).

It also makes sense to use arrangements of elements that are joined together by wringing. The fact that the absolute
20 amount of birefringence is larger in crystalline quartz is of practical significance because less of the SiO_2 crystal is needed for compensation. Also, crystalline SiO_2 has the smaller index of refraction and its use at the image-oriented end of a high-aperture immersion objective is therefore less
25 advantageous.

An arrangement that is suitable for example for a wavelength of 193 nm is shown in Figure 5. The spaces between the lenses, particularly in the area near the image plane where
30 there are large ray angles relative to the optical axis, can be filled by high-refractive fluids FL1 of the same kind that are also used as an immersion medium. A double arrow in the lenses indicates the orientation of the optical axis of the birefringence that is inherent in the materials.

It is clear that the effective index of refraction in the crystals Al_2O_3 and SiO_2 is subject to a continuous angle-dependent variation, but with tangentially polarized light
5 there is initially no phase shift between an s-polarized and a p-polarized component. The variation of the refractive index is taken into account in the design.

Figure 6 illustrates an example of an objective for an
10 operating wavelength of 157 nm with CaF_2 lenses of different crystallographic orientation, for example 111 and 110, for the compensation of intrinsic birefringence with a pair of optically uniaxial crystal lenses that is compensated in accordance with the invention. With immersion I or the near-
15 field lithography technique, the objective can be coupled to the object to be exposed, for example a wafer W, with the largest possible numerical aperture.

Because of the high light-gathering power (etendue), it is
20 preferred to make the compensation. This is the best way to master the problem of extended fields outside of the telecentric light path without the split between s-polarization and p-polarization. Of course, with a skewed incident radiation in birefringent crystals, the n_e -components
25 run outside the plane of incidence. However, with the different character of SiO_2 crystal and Al_2O_3 sapphire, it is possible to take specifically targeted countermeasures.

The term "negative optical character" means that the
30 refractive index n_o of the ordinary ray is larger than the refractive index n_e of the extraordinary ray.

The term "positive optical character" means that the refractive index n_o of the ordinary ray is smaller than the refractive index n_e of the extraordinary ray.

5 The scope of the invention includes: the compensation as described; the use of Al_2O_3 , sapphire and SiO_2 crystal in lithography optics; the placement of the elements between the aperture stop or a conjugate location of the aperture stop and the image plane of a projection objective, with special
10 preference for placing these elements in the bottom one-third of the distance between the aperture stop and the image plane; the use of the aforementioned materials for protector plates for immersion or near-field arrangements, either by themselves without compensation, or with compensation; the
15 use at high angles of incidence $>60^\circ$, with special preference $>70^\circ$; including in these applications the compensation at the highest numerical aperture values NA (above 1.3 to 1.6) on the image side; also including the use of tangentially polarized light; and further including the use in immersion
20 objectives with a refractive index of more than 1.8 in the last optical element, with special preference for more than 2.0; and also the use at an operating wavelength of 157 nm in conjunction with the crystals CaF_2 , SiO_2 , Al_2O_3 , sapphire - in respectively different combined arrangements.

25 Similar to silicon dioxide, magnesium fluoride in crystalline form has an optically positive character. The advantage of MgF_2 lies in its high UV transmittance, particularly at 157 nm. Its drawback is the low coefficient of refraction,
30 for example at a wavelength of 193.304 nm, with values of $n_o = 1.427460$ and $n_e = 1.441069$.

The compensation of birefringence in a high-aperture end-closure part of a microlithographic projection objective .

requires the availability of suitable degrees of freedom. If the birefringence were of exactly equal magnitude and had the same form in Al_2O_3 as in quartz crystal, an exact solution that provides compensation for all angles would exist at least for planar-parallel plates, i.e., one would only need to use two plates of equal thickness. If lenses are used instead of plates, the possible phase differences occurring as a result of refraction and birefringence become larger and there is an increased risk that this will affect the image quality. On the other hand, with lenses one has the possibility to use a targeted variation of the radii as a further degree of freedom in addition to the thickness, as a parameter for compensation.

Based on these considerations, a further material is proposed for an additional fine correction, namely MgF_2 crystal. In view of its low index of refraction, it is placed preferably in a position before the more strongly refractive elements of quartz crystal and sapphire. It should be noted in this context that the uniaxial birefringent crystals Al_2O_3 , sapphire, SiO_2 , MgF_2 are compensated in an entirely different manner than the CaF_2 , SrF_2 , and BaF_2 crystals and the like which are a priori isotropic (at least in the visible range).

The refractive index of the successive elements, for example at the 157 nm wavelength in the example of Figure 7, is continuously increased towards the wafer (image plane), namely up to a level of more than 2.0.

The optical path lengths for s-and p-polarization are largely equalized for the broadest possible range of angles through the simultaneous use of three crystalline materials Al_2O_3 , SiO_2 , and MgF_2 . It should be noted that the harmful contributions for skewed rays increase the farther one moves

these elements away from the wafer, i.e., from the image plane. This also provides the special possibility of a compensation based on where a lens of each of the respective materials is positioned. The optical path length should to
5 the greatest extent possible meet the condition
$$(n_o - n_e)Al_2O_3 \cdot d_1 + (n_o - n_e)SiO_2 \cdot d_2 + (n_o - n_e)MgF_2 \cdot d_3 = 0,$$
wherein n_o represents the refractive index for the ordinary ray, n_e represents the refractive index for the extraordinary ray, and d_1 , d_2 , d_3 represent the respective path lengths
10 inside the crystals. It should be the aim (and it is possible) to meet the condition particularly well in the aperture angle range from 65° to 72°.

The scope of the invention likewise includes a lithography
15 objective in a projection system, where the effect of birefringence of uniaxial crystal materials in end-closure plates or lenses on the image side of the objective is completely corrected for angles in the range from 65° to 72° (measured geometrically from the optical axis).

20 Instead of using Al_2O_3 sapphire for the compensation or as a provider for the primary refractive power in this end range, one could also use the uniaxial crystal material LaF_3 as a further possible lens material. Like Al_2O_3 , it has a negative
25 optical character and the birefringence values likewise resemble those of Al_2O_3 . In comparison to sapphire, LaF_3 has the advantage that the commercially available crystals, which are made in a completely different manufacturing process, currently meet higher standards of optical quality. LaF_3 is
30 water-insoluble, but it does not come up to the levels of hardness and UV transmittance of Al_2O_3 sapphire.

Figure 8 schematically illustrates an example for an operating wavelength of 193 nm where LaF_3 is used for the last

lens on the image side, in this case with a protector plate P of α - Al_2O_3 . In this case, too, the alternative to an arrangement with an immersion fluid is an optical near field where the distance between the protector plate P and the
5 wafer is shorter than the operating wavelength.

With this plate P of Al_2O_3 , it is very important to pay attention to the fact that the α -modification of the crystal represents the advantageous choice. The γ -modification of
10 Al_2O_3 is hygroscopic and should not be used.

Table 1:

Refractive indices of the uniaxial crystals

MgF ₂		
wavelength	ordinary	extraordinary
248.338 nm	1.403248	1.416080
193.304 nm	1.427460	1.441069
157.629 nm	1.466666	1.481281

SiO ₂		
wavelength	ordinary	extraordinary
248.338 nm	1.601568	1.612689
193.304 nm	1.660455	1.673963

Difference between indices $\Delta n = n_o - n_e$

157.629 nm	Al ₂ O ₃	0.012973
	MgF ₂	0.014243

- 5 The birefringence values were measured by the interference method and are more reliable than measuring the indices n_o and n_e by means of prisms and taking the differences. In regard to this topic, reference is also made to an article in Applied Optics, March 1969, Volume 8 No. 3, p. 673, where the
- 10 wavelength-dependent variation of n_o and n_e is discussed.

Figure 9 is copied from Fig. 3 of the aforementioned reference.

- 15 Further according to the invention, uniaxial crystals are compensated as follows:

Lenses LPP of positive refractive power and positive optical character are compensated by lenses LPN of positive

20 refractive power with negative character (Fig. 10). In

addition, lenses of positive refractive power can also be compensated with lenses of negative refractive power with the same character, as shown in the example of Figure 11 - with positive character in the lenses LPP, LNP (negative

5 refractive power), possibly supplemented by a lens LPN.

Figure 12 shows an arrangement where lenses LPN, LNN, LPP follow each other, with LNN being a lens of negative refractive power and negative optical character.

10 As a further example, Figure 13 shows the four last lenses on the image side of a microlithography projection objective with the materials according to the invention as the significant mass (material) of the lenses, which may be coated with layers for antireflection, anticorrosion or the
15 like (as in the other embodiments discussed), i.e., MgF_2 / SiO_2 crystal / optional fluid lens / LaF_3 / Al_2O_3 sapphire, and with appropriate compensation of imaging errors due to birefringence effects of the lens materials.


Patent Claims:

1. Microlithography projection objective with at least one
lens of quartz crystal and with at least one lens of
5 sapphire crystal.
2. Microlithography projection objective with at least two
transmittent optical elements, in particular lenses (L)
or planar-parallel plates (P) consisting of crystals that
10 are uniaxial with regard to birefringence, wherein at
least two of said optical elements consist of different
crystal materials.
3. Microlithography projection objective according to claim
15 1 or claim 2, characterized in that an axis of
birefringence of a first optical element and an axis of
birefringence of a second optical element each run
parallel to the optical axis of the geometrical light ray
path inside the projection objective.
20
4. Microlithography projection objective according to at
least one of the preceding claims, characterized in that
said lenses (L) or optical elements (P) are arranged on
the image side of a pupil or system aperture (AS) that is
25 nearest to the image plane.
5. Microlithography projection objective according to at
least one of the preceding claims, characterized in that
said lenses (L) or optical elements (P) are among the
30 three optical elements that lie closest to the image
plane (W).
6. Microlithography projection objective according to at
least one of the preceding claims, characterized in that

the numerical aperture on the image side is larger than 1.6 and with special preference larger than 1.8.

7. Microlithography projection system with a
5 microlithography projection objective according to at least one of the claims 1 to 6.
8. Microlithography projection system according to claim 7,
10 characterized in that polarized light passes through said crystalline lenses or crystalline optical elements.
9. Microlithography projection system according to claim 8,
15 characterized in that the light is tangentially polarized.
10. Microlithography projection system according to claim 8,
characterized in that the light is linearly polarized.
11. End-closure plate of a microlithography projection
20 objective substantially made of $\alpha\text{-Al}_2\text{O}_3$.
12. Use of an LaF_3 lens or LaF_3 planar-parallel plate in a microlithography projection objective.
13. Microlithography projection objective with at least two
25 optical elements from the group that comprises lenses and planar-parallel plates substantially consisting of a material from the group that comprises crystals of MgF_2 , SiO_2 , LaF_3 , sapphire, $\alpha\text{-Al}_2\text{O}_3$.
30
14. Microlithography projection objective according to claim 13, characterized by the presence of two or three different materials selected from said group of crystals.

1/9

FIG.1

•

•

•



•

•


•

•


3/9

FIG.4**FIG.5**


4/9

FIG.6

5/9

FIG.7

6/9

FIG.8

7/9


FIG.9

FIG.10







FIG.11



9/9

FIG.12**FIG.13**

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
30 June 2005 (30.06.2005)


PCT

(10) International Publication Number
WO 2005/059645 A3

- (51) International Patent Classification⁷: **G03F 7/20**, (72) Inventor; and
G02B 13/14 (75) Inventor/Applicant (for US only): SCHUSTER, Karl-
Heinz [DE/DE]; Rechbergstrasse 24, 89551 Königsbronn
(DE).
- (21) International Application Number: PCT/EP2004/014100 (74) Agent: MÜLLER-RISSMANN, Werner; c/o Carl Zeiss
AG, Patentabteilung, 73446 Oberkochen (DE).
- (22) International Filing Date: 10 December 2004 (10.12.2004) (81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/530,623 19 December 2003 (19.12.2003) US
60/568,006 4 May 2004 (04.05.2004) US
- (71) Applicant (for all designated States except US): CARL
ZEISS SMT AG [DE/DE]; Carl Zeiss Str. 22, 73447
Oberkochen (DE). (84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,

[Continued on next page]

(54) Title: MICROLITHOGRAPHY PROJECTION OBJECTIVE WITH CRYSTAL ELEMENTS



(57) Abstract: A microlithography projection objective is proposed with optical elements, i.e. lenses or planar-parallel plates (used as end-closure plates) of crystalline magnesium fluoride, quartz, lanthanum fluoride, sapphire and Alpha-aluminium oxide. Suitable crystallographic orientations, crystal 10 combinations, and polarizations of the light are described. Suitable applications are for immersion lithography or near-field lithography in the DUV and VLN range, using the highest numerical aperture values.

WO 2005/059645 A3



GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations
- of inventorship (Rule 4.17(iv)) for US only

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE,

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the International search report:

20 October 2005

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

INTERNATIONAL SEARCH REPORT

International Application No
PC1/EP2004/014100

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 G03F7/20 G02B13/14

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 G03F G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, INSPEC

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2003/168597 A1 (WEBB JAMES E ET AL) 11 September 2003 (2003-09-11)	1-10, 12-14
Y	paragraphs '0003! - '0006!, '0013!, '0026!, '0047!, '0050!, '0055! - '0057!, '0060!, '0061!, '0066!; figures 1,4,8,9	11
X	EP 1 083 444 A (NIKON CORPORATION) 14 March 2001 (2001-03-14) paragraphs '0064!, '0065!	2,7,12, 13
X	US 6 291 110 B1 (COOPER GREGORY D ET AL) 18 September 2001 (2001-09-18) column 9, line 4 - line 10; figure 8	11
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

8 document member of the same patent family

Date of the actual completion of the international search

11 August 2005

Date of mailing of the international search report

29/08/2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Eisner, K

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2004/014100

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 03/093904 A (CARL ZEISS SMT AG; SCHUSTER, KARL-HEINZ) 13 November 2003 (2003-11-13) page 18, line 16	11
P,X	WO 2004/013674 A (ASML HOLDING N.V; SEWELL, HARRY) 12 February 2004 (2004-02-12) paragraph '0042!	2,7,12, 13

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP2004/014100

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 2003168597	A1	11-09-2003	AU 2003230595 A1	22-09-2003
			EP 1521990 A2	13-04-2005
			WO 03076978 A2	18-09-2003
EP 1083444	A	14-03-2001	EP 1083444 A1	14-03-2001
			JP 2001147302 A	29-05-2001
			US 6495202 B1	17-12-2002
US 6291110	B1	18-09-2001	AU 8375798 A	19-01-1999
			CA 2295635 A1	07-01-1999
			EP 0991982 A1	12-04-2000
			JP 2002511980 T	16-04-2002
			WO 9900706 A1	07-01-1999
			US 2002176062 A1	28-11-2002
			US 2004051855 A1	18-03-2004
			US 2002027647 A1	07-03-2002
WO 03093904	A	13-11-2003	AU 2003232226 A1	17-11-2003
			WO 03093904 A1	13-11-2003
			EP 1502158 A1	02-02-2005
			US 2004004757 A1	08-01-2004
			US 2005111108 A1	26-05-2005
			AU 2002312872 A1	22-09-2003
			DE 10224361 A1	13-11-2003
			EP 1483625 A1	08-12-2004
			JP 2005519347 T	30-06-2005
			US 2005030506 A1	10-02-2005
			US 2005141098 A1	30-06-2005
WO 2004013674	A	12-02-2004	US 2004021943 A1	05-02-2004
			AU 2003254293 A1	23-02-2004
			CN 1564958 A	12-01-2005
			EP 1527364 A1	04-05-2005
			JP 2005520355 T	07-07-2005
			WO 2004013674 A1	12-02-2004